

Ddev Plastiks Industries Limited TECHNICAL DATA SHEET

KI - 90 (3V90) AS NZS RoRE: Heat resistant PVC Cable Compound

Description:

KI — 90 (3V90) AS NZS RORE is a special type heat resistant compound for sheathing applications in a wide variety of cables. **KI — 90 (3V90) AS NZS RORE** is formulated with a high-quality resin with plasticizers, stabilizers. It is RoHS + REACH compliant.

Specification:

AS/NZS 3808:2000 – 3V90 (Sheathing)

Colour: Natural/as per requirement

Typical Properties:

Property		Unit	Test Method	Typical Value
Sp. Gravity @27°C			ASTM - D - 792	1.28 ± 0.03
Hardness @27°C		Shore A	ASTM - D 2240	50 ± 2
Thermal Stability@200°C		Minutes	IS: 10810 (60)	≥ 100
Tensile Strength (TS) @27°C		MPa	IS: 10810 (7)	≥ 7.0
Elongation at Break (E.B) @27°C		%	IS: 10810 (7)	≥ 160
Ageing Test	Temperature	°C		115
	Duration	Hr		504
Variation of T.S		%	IS: 10810 (11)	≤ ± 25.0
Variation of E.B		%	IS: 10810 (11)	≤ ± 35.0
Mass Loss on Ageing (115°C / 120 Hrs)		mg/cm ²	IS: 10810 (10)	≤ 2.5

^{*} Test specimen made after milling the granules and the compression molded at 160 °C for 10 min with 200kg / cm² hydraulic pressure

Above Values are Typical value of Compound and customer need to check before accepting the TDS.

Processing:

KI – 90 (3V90) AS NZS RoRE can be processed on any good extruder designed for PVC cable extrusion at temperature in the range of 140° C- 180° C. This is the guideline temperature range; actual temperature should be optimized by the user depending upon the other processing variables. The screw must have a good homogenizing capacity. Preheating of granules at $80+/-5^{\circ}$ C is always advisable for better processing.

Packaging:

KI – 90 (3V90) AS NZS RORE is available in the form of free-flowing pellets and supplied in bags with sealed double layer PE liner to prevent moisture. The finished bag weight is either 25 kg woven sacks bag or in 1000kg jumbo bags.

Material should be store in moisture free cool & dry place.

Safety:

KI - 90 (3V90) AS NZS RORE is not classified as a dangerous product group.

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. These are all the typical values only and subject to change without prior intimation. The product is sold upon condition that purchaser should make their own tests to determine the suitability of such product of their particular purpose and purchasers assume all risks and liability for the results of the use of the product.

For more information pl contact at;

Head Office:

2B Pretoria Street, Kolkata-71 Tel: 91-33-22823744/45/3671 Fax:91-33-22823739

E-mail: kolkata@ddevgroup.in Website: www.ddevgroup.in Works:

Survey No: 24/3, Demni Road, Village-Demni Dadra(Dadra & Nagar Haveli)-396 193, India Tel:91-9909006426

E-mail:dadra@ddevgroup.in

Mumbai Office

106, Laxmi Plaza, Laxmi Industrial Estate New Link Road, Andheri(West) Mumbai-400053, India

E-mail: mumbai@ddevgroup.in